



Peak load test

(DO 9.21-4320, IEC EN 61386)

This standard describes the peak load test on conduits under standard ambient conditions (23°C/50% relative humidity). The conduit is deformed by a defined amount between two plates. The restoring force established over a specific time (by relaxation of the conduit) describes the crushing pressure or compressive strength.